VENABIO[®] BRAI DOUBLE BRAIDED

This product is braided twice using a polyester yarn and pressure resistance and a maximum of 180°C.

MATERIAL

Platinum cured silicone. Postcured to completely eliminate volatiles. Reinforced with a polyester or fiberglass braiding.

Hardness	Shore A	60
Tensile strength	N/mm²	>7
Elongation	%	>300
Tear strength	kN/m	>20
Density	g/cm³	1,17

DESCRIPTION

Silicone tubing is the basic material upon any single use process is built.

Its great overall performance and resistance to temperature, moist, ozone and steam and high biocompatibility makes it the product of choice for all stages of bioprocessing, from drug formulation, upstream processing and all downstream's critical steps from separation to final fill.



ROLL LENGTH Available in 25ft and 50ft



CLEAN ROOM Manufactured in ISO14644-1 Class 7



TEMPERATURE -60°C/+180°C $(-76^{\circ}F/+356^{\circ}F)$



SMOOTHNESS Reduces protein binding and biofilm formation



LASER ETCHED Traceable with reference, lot number and ID/OD



DOUBLE BAG Double bagged under vacuum (see page 5)



ANIMAL FREE Animal derived component free



RADIOSTABLE Gamma/eBeam sterilization available

STERILIZATION

- O Dryheat
- O Autoclave
- O CIP
- O SIP
- O Ethylene oxide
- O Hydrogen peroxide
- eBeam (25kGy)*
- O Gamma (25kGy)*

*Sterilization available prior shipment.

BIOCOMPATIBILITY*

- O ADCF
- O P/BPA
- O BSE/TSE
- O EU 10/2011
- O EU 1935/2004
- O BfR XV
- O 3A18-03
- O EP 3.1.9.
- O FDA 21CFR177.2600
- O USP85
- O USP 87
- O USP 88
- O USP381
- O USP788
- O ISO10993-4
- O ISO10993-5
- O ISO10993-6
- O ISO10993-10
- O ISO10993-11
- O Extractables & leachables

*For complete validation package, please contact your sales representative.

MORE VENABIO®

- O Silicone:
 - Flow Pumpgrade
 - Flow Multipurpose
 - Flow High Pressure
 - Precision
 - Braided
 - Braided Plus
 - Braided High Pressure
- O Thermoplastics:
 - Weld
 - Pump
- O Fluorinated
 - FEP
 - PTFE

Reference	ID	OD	Wall	Working pressure	Burst pressure
9200855*	mm (inches)	mm (inches)	mm (inches)	Bar (PSI) at 20°C	Bar (PSI) at 20°C
920085500005	5,10 (1/5)	13,10 (33/64)	4,00 (3/19)	25,2 (365)	75,5 (1095)
920085500006	6,40 (1/4)	16,10 (45/71)	4,85 (17/89)	23,7 (344)	71,2 (1033)
920085500008	7,90 (5/16)	18,00 (17/24)	5,05 (1/5)	22,9 (331)	68,5 (994)
920085500010	9,50 (3/8)	20,00 (37/47)	5,25 (6/29)	22,3 (324)	66,9 (971)
920085500012	12,70 (1/2)	22,70 (42/47)	5,00 (12/61)	19,4 (282)	58,3 (846)
920085500015	15,90 (5/8)	27,10 (1 1/15)	5,60 (15/68)	17,0 (246)	50,9 (739)
920085500019	19,10 (3/4)	30,60 (1 17/83)	5,75 (12/53)	15,6 (226)	46,8(678)
920085500022	22,20 (7/8)	33,20 (1 4/13)	5,50 (21/97)	14,0 (202)	41,9 (607)
920085500025	25,40 (1)	37,00 (1 37/81)	5,80 (8/35)	12,5 (181)	37,5 (544)
920085500028	28,00 (1 4/39)	41,60 (1 44/69)	6,80 (15/56)	11,7 (169)	35,0 (508)
920085500032	31,80 (1 1/4)	46,10 (1 22/27)	7,15 (9/32)	10,1 (164)	30,2 (438)

IMPORTANT: The Company reserves the right to change, amend, modify, suspend, continue or terminate all or any part of this Catalogue at any time without notice. It is the user's responsibility to ensure the suitability and safety of the VENAIR products for all intended uses. All the tests must be conducted in accordance with applicable regulatory requirements in order to determine the safety and effectiveness for use of the hoses in any particular application.

LIMITED WARRANTY: For a period of 6 months from the date of sale, VENAIR warrants this product to be free from defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risk, if any, including the risk of injury, loss or damage, direct or consequential, arising out of the use, misuse, or inability to use, this product. This warranty is in lieu of the warranties of merchantability, fitness for particular purpose, and all other warranties, expressed implied. No deviation is authorized. VENAIR assumes no obligations on liability for any advice furnished by it, or for results obtained with respect to those products. All such advice is given and accepted at the buyer's risk.

Vena, Venair and the Venair logo are trademarks of Venair Ibérica SA.

BROCH 2 REV 02 EN Copyright 2020 |Venair Group |All Rights Reserved

