

Vena® SIL 200

Ref: DO 03.10 FT 01. Rev. 12
Date: 20/06/2017



Limitations

Respect the work pressure established values.

Gas oil and oil stains do not damage the tubes, but they should not be used to transport fuel or oil, nor be submerged in these liquids.

This type of tube is not recommended for applications with negative pressure (vacuum).

This product is not recommended for the transport of abrasive particles.

Regulations

- Meets or exceeds operating requirements of SAE J20 R1 Class A.
- Silicone rubber used is in accordance with EU Directive 2002/95/ECC for Restriction of the use of hazardous substances (RoHS).

Applications

It is especially recommended for pressurized air or water conduction at high temperatures, it can be used in vehicles and in the industrial sector.

For use in cooling and heating systems in buses, coaches, trucks, industrial vehicles, cooling systems in cogeneration units and marine engines, and transport of high temperature fluids in general industry.

It is recommended for the use in straight sections without curves.

Properties

- Not affected by anti-freeze or antirust liquids.
- Highly resistant to hardening with very good compression characteristics.
- Excellent flexibility during the assembly process.
- Smooth inner and outer appearance, and blue color. Upon request, it can also be supplied in other colors (red, green, black...).
- Excellent resistance to thermal aging and oxidizing agents (oxygen, ozone, UV).
- Operational temperature range from -60°C (-75 F) to +180°C (356 F), it may reach up to 200°C (392 F) during short periods of time.
- The standard manufacturing length is 4 meters long (13.12 ft.), although it is available in shorter lengths if necessary.

Construction

- This reference is manufactured with three polyester fabric reinforcements.

Alternatives:

SIL 200 RA: The inner layer could be made in R/A silicone, that could resist oil drops in this case the inner layer is brown red colored.

SIL 200 FVMQ: The inner layer could be made in black FVMQ silicone, that has high capacity to withstand hydrocarbons and oil particles.

SIL 200 FKM: The inner layer could be made in black FKM, that it has a higher resistance to oil particles and/or hydrocarbons in suspension.

Technical Specifications



Inner Diameter		Wall thickness		Working Pressure ISO 1402/2009		Bursting Pressure ISO 1402/2009	
<i>mm</i>	<i>inch</i>	<i>+1/ -0.5 mm</i>	<i>+0.04/ -0.02 inch</i>	<i>Bar at 20°C</i>	<i>Psi at 68°F</i>	<i>Bar at 20°C</i>	<i>Psi at 68°F</i>
6	1/4	4.30	0.17	16.2	234.4	48.5	703.3
13	1/2	4.30	0.17	9.7	140.6	29.1	421.7
19	3/4	4.30	0.17	7.3	105.4	21.8	316.1
25	1	4.30	0.17	5.9	85.6	17.7	256.7
32	1 1/4	4.30	0.17	4.9	70.8	14.7	212.5
38	1 1/2	4.30	0.17	4.3	62.2	12.9	186.5
45	1 3/4	4.30	0.17	3.8	54.7	11.3	164.0
51	2	4.30	0.17	3.4	49.7	10.3	149.1
57	2 1/4	4.30	0.17	3.2	45.7	9.5	137.0
63	2 1/2	4.30	0.17	2.9	42.3	8.8	127.0
70	2 3/4	4.30	0.17	2.7	39.1	8.1	117.2
76	3	4.30	0.17	2.5	36.5	7.6	109.5
80	3 1/8	4.30	0.17	2.3	33.6	7.0	100.8
90	3 1/2	4.30	0.17	1.9	27.8	5.7	83.2
100	4	4.30	0.17	1.7	23.9	5.0	71.8